

## be.tex® Samba® FR | Product no.: 4384-6266

Woven



### PRODUCT FEATURES

Material: 100% polyester  
Weight: 195 g/m<sup>2</sup>  
Thickness: 250 µm  
Stretch: < 1 %  
Transmission factor: 38 %  
Whitepoint: 94, 1, -6 L\*a\*b

### WIDTH (cm)

ca. 160  
ca. 260  
ca. 320

### LENGTH (m)

ca. 70  
ca. 100  
ca. 100



### APPLICATIONS

inflatables  
display frame systems  
light boxes  
pop up display systems  
bean bags  
table cloth  
banners  
tents / parasols

### FEATURES

air tight  
water tight  
no fraying  
good flatness  
crease free  
lotus effect  
light diffusion coating

### DESCRIPTION

Topseller and market standard for light boxes. Perfect backlighting characteristics and color-intensive print features. Absolutely crease free, therefore perfect for folded shipment, sun umbrellas, tents, blow-ups, beanbags, lightboxes, aluframes, etc. be.tex® Samba FR is even unlit and unprinted an absolute allrounder. Uncoated side with Lotus-effect. Water column coated side > 900 mm, uncoated side > 650 mm.

### NOTES

*The numbers above are purely guidelines and may differ depending on your personal printing needs and expectations. Since the printing results depend on numerous factors, we strongly advise to test your output in order to find out if any adjustments are necessary. A legally binding assurance of certain properties of the fabric can not be derived from the information above.*

# PRODUCTDATA

## Digital

Last change: January 17, 2019



Dye sub paper transfer on uncoated side: self-tests are recommended. For Latex prints with a very high ink-load (backlit) self-tests are recommended. Do not use self-adhesive products as flat profile 4545-1sk for processing (lotus on the back). Technical textiles are naturally subject to weather conditions. This product can be used outdoor for a short term. When handled carefully this fabric can be even folded after printing.

*The numbers above are purely guidelines and may differ depending on your personal printing needs and expectations. Since the printing results depend on numerous factors, we strongly advise to test your output in order to find out if any adjustments are necessary. A legally binding assurance of certain properties of the fabric can not be derived from the information above.*